

Fine-grain structural steels, normalized rolled

1.049	S275N	StE 285		Fe E 275 KGN			A 572 Gr. 42	
1.0491	S275NL	TStE 285		Fe E 275 KTN	43 EE		A 633 Gr. A	
1.0545	S355N	StE 355	E 355 R	Fe E 355 KGN	50 E	AE 355 KG	A 572 Gr. 50	
1.0546	S355NL	TStE 355	E 355 FP	Fe E 355 KTN	50 EE	AE 355 KT	A 633 Gr. C, D / A 537 Cl. 1	
1.8902	S420N	StE 420	E 420 R	Fe E 420 KGN		AE 420 KG	A 255 Gr. D	SM 490 A
1.8912	S420NL	TStE 420	E 420 FP		50 F		A 633 Gr. E / A 572 Gr. 60 / A 738 Gr. C	