



ROLF

ENGG. SOLUTIONS INC.



Manufacturer & Exporters of
High Tensile Carbon Steel, API 5L X52 to X70 PSL 1/2, LSAW, ERW & Seamless Pipes & Fittings,
Stainless Steel, Alloy Steel Pipes & Fittings, High Nickel Alloys, Monel, Inconel, Hastelloy, SM0254,
Duplex, Super Duplex, Titanium-B2, B5 - Pipes & Fittings, Finned Tubes, Studded Pipes.

Designation: A 194/A 194M - 08

Approved by
Manufacturers Standardization Society
of the Valve and Fittings Industry
Used in USNRC-RDT Standards

NT6/SHATTO#A

Standard Specification for Carbon and Alloy Steel Nuts for Bolts for High Pressure or High Temperature Service, or Both'

This standard is issued under the fixed designation A 194/A 194M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers a variety of carbon, alloy, and martensitic stainless steel nuts in the size range $\frac{1}{4}$ through $\frac{3}{4}$ in. and metric M6 through M100 nominal. It also covers austenitic stainless steel nuts in the size range $\frac{1}{8}$ in. and M6 nominal and above. These nuts are intended for high-pressure or high-temperature service, or both. Grade substitutions without the purchaser's permission are not allowed.

1.2 Bars from which the nuts are made shall be hot-wrought. The material may be further processed by centerless grinding or by cold drawing. Austenitic stainless steel may be solution annealed or annealed and strain-hardened. When annealed and strain hardened austenitic stainless steel is ordered in accordance with Supplementary Requirement 51, the purchaser should take special care to ensure that 5.2.2, Supplementary Requirement S1, and Appendix XI are thoroughly understood.

1.3 Supplementary requirements (SI through 58) of an optional nature are provided. These shall apply only when specified in the inquiry, contract, and order.

1.4 This specification is expressed in both inch-pound units and in SI units. However, unless the order specifies the applicable "M" specification designation (SI units), the material shall be furnished to inch-pound units.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. Within the text, the SI units are shown in brackets.

2. Referenced Documents

2.1 ASTM Standards: -'

A 153/A 153M Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware

A 276 Specification for Stainless Steel Bars and Shapes

A 320/A 320M Specification for Alloy-Steel and Stainless Steel Bolting Materials for Low-Temperature Service

A 962/A 962M Specification for Common Requirements for Steel Fasteners or Fastener Materials, or Both, Intended for Use at Any Temperature from Cryogenic to the Creep Range

B 695 Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel

B 696 Specification for Coatings of Cadmium Mechanically Deposited

B 766 Specification for Electrodeposited Coatings of Cadmium

E 112 Test Methods for Determining Average Grain Size

F 1940 Test Method for Process Control Verification to Prevent Hydrogen Embrittlement in Plated or Coated Fasteners

F 1941 Specification for Electrodeposited Coatings on Threaded Fasteners (Unified Inch Screw Threads (UN/UNR))

2.2 American National Standards.

B 1.1 Unified Screw Threads

B 1.2 Gages and Gaging for Unified Inch Screw Threads

B 1.13 Metric Screw Threads

B 1.8.2.2 Square and Hex Nuts

B 18.2.4.6M Metric Heavy Hex Nuts

3. Terminology

3.1 Definitions of Terms Specific to This Standard.

" For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at servicet@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

' Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

* This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved April 1, 2008. Published May 2011. Originally approved in 1936. Last previous edition approved in 2007 as A 194/A 194M - 07b.

For ASME Boiler and Pressure Vessel Code applications see related Specification SA-194 in Section 11 of that code.

***A Summary of Changes section appears at the end of this standard.**

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

3.1.1 *Austenitic Grades*—All grades with a prefix of “8” or “9”.

3.1.2 *Ferritic Grades*—Grades 1, 2, 2H, 2HM, 3, 4, 6, 6F, 7, 7M, and 16.

3.1.3 *Lot*—Unless otherwise specified (see Discussion below), a Lot is the quantity of nuts of a single nominal size and grade produced by the same manufacturing process.

3.1.3.1 *Discussion*—When Supplementary Requirement 55 is invoked on the purchase order, the following definitions of a lot shall apply:

3.1.3.2 *For Grade 8 Nuts*—The quantity of all the nuts of a single nominal diameter and grade made from the same heat of steel and made by the same manufacturing process.

3.1.3.3 *For All Other Grade Nuts*—(see 8.2 and 8.1.2.1)—All the nuts of a single nominal diameter and grade made from the same heat number and heat treated in the same batch if batch-type heat treating equipment is used or heat treated in the same continuous run of not more than 8 h under the same conditions if continuous-type heat treating equipment is used.

3.1.4 Type

3.1.4.1 *For Grade 8 buff*—Variations within the grade designated by a letter and differentiated by chemistry and by manufacturing process.

3.1.4.2 *For Grade 6 'me*—Variations within the grade designated by the letter F as differentiated by chemical additions made for machineability.

3.1.5 *Series*—The dimensional relationship and geometry of the nuts as described in ANSI B 18.2.2 or B 18.2.4.6M.

4. Ordering Information

4.1 The inquiry and order for material under this specification shall include the following as required to describe the material adequately:

4.1.1 Specification designation, year date, and grade, issue date and revision letter,

4.1.2 Quantity, number of pieces,

4.1.3 Dimensions (see Section 9),

4.1.4 Options in accordance with 8.2.2.1, 9.1, 9.2, 10.3, and 12, and

4.1.5 Supplementary Requirements, if any.

4.2 *Coatings*—Coatings are prohibited unless specified by the purchaser (see Supplementary Requirements S7 and S8). When coated nuts are ordered, the purchaser should take special care to ensure that Appendix X2 is thoroughly understood.

4.3 See Supplementary Requirement 53 for nuts to be used in low temperature applications (Specification A 320/A 320M).

5. Common Requirements

5.1 Material and fasteners supplied to this specification shall conform to the requirements of Specification A 962/A 962M. These requirements include test methods, finish, thread dimensions, marking, certification, optional supplementary requirements, and others. Failure to comply with the requirements of Specification A 962/A 962M constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification A 962/A 962M, this specification shall prevail.

6. Manufacture (Process)

6.1 Stainless steels for all types of Grade 6 and 8 nuts shall be made by one of the following processes:

6.1.1 Electric-furnace (with separate degassing and refining optional),

6.1.2 Vacuum induction furnace, or

6.1.3 Either of the above followed by electroslag remelting, or consumable-arc remelting.

6.2 The steel producer shall exercise adequate control to eliminate excessive unhomogeneity, nonmetallics, pipe, porosity, and other defects.

6.3 **Grades 1 and 2** nuts shall be hot or cold forged, or shall be machined from hot-forged, hot-rolled, or cold-drawn bars.

6.3.1 All Grade 1 and 2 nuts made by cold forging or by machining from cold-drawn bars shall be stress-relief annealed at a temperature of at least 1000 °F [538 °C].

6.3.2 Grade 1 and 2 nuts made by hot forging or by machining from hot-forged or hot-rolled bars need not be given any stress relief annealing treatment.

6.4 Grades 2H, 2HM, 3, 4, 6, 6F, 7, 7M, and 16 nuts shall be hot- or cold-forged or shall be machined from hot-forged, hot-rolled, or cold-drawn bars and shall be heat treated to meet the required mechanical properties. These grades shall be reheated above the critical range of the steel, quenched in a suitable medium, and then tempered at a temperature not less than the following:

Grade	Minimum Tempering Temperature, °F [°C]
2H	850 [455]
2HM	1150 [620]
3	1050 [565]
4	1100 [595]
6 and 6F	1100 [595]
7	1100 [595]
7M	1150 [620]
6	1200

Nuts machined from bar heat treated in accordance with this specification need not be reheat-treated. For Grade 2HM and 7M nuts, a final stress relief shall be done at or above the minimum tempering temperature after all forming, machining, and **tapping** operations. This final stress relief may be the tempering operation.

6.4.1 Grade 6 and 6F nuts shall be tempered for a minimum of 1 h at the temperature.

6.5 Grades 8, 8C, 8M, 8T, 8F, 8P, 8N, 8MN, 8R, 8S, 8LN, 8MLN, 8MLCuN, and 9C nuts shall be hot or cold forged, or shall be machined from hot-forged, hot-rolled or cold-drawn bars.

6.6 Grades 8A, 8CA, 8MA, 8TA, 8FA, 8PA, 8NA, 8MNA, 8RA, 8SA, 8LNA, 8MLNA, 8MLCuNA, and 9CA nuts shall be hot- or cold-forged or shall be machined from hot-forged, hot-rolled, or cold-drawn bars and the nuts shall subsequently be carbide-solution treated by heating them for a sufficient time at a temperature to dissolve chromium carbides followed by cooling at a rate sufficient to prevent reprecipitation of the carbides.

7. Chemical Composition

7.1 Each alloy shall conform to the chemical composition requirements prescribed in Table 1.

SKE 280608

A 194/A 194M—08

TABLE 1 Chemical Requirements**

Grade Symbol	Material	UNS Number	Carbon, %	Manganese, %	Phosphorus, %	Sulfur, %	Silicon, %	Chromium, %	Nickel, %	Molybdenum, %	Titanium, %	Columbium and Tantalum, %	Nitrogen, %	Other Elements, %
1	carbon		0.15 min	1.00	0.040	0.050	0.40							
2, 2HM, and 2H	carbon		0.40min	1.00	0.040	0.050	0.40							
4	carbon, molybdenum		0.40--0.50	0.70--0.90	0.035	0.040	0.15--0.35			0.20--0.30	...			
3	Type 501		0.10 min	1.00	0.040	0.030	1.00	4.0--6.0		0.40--0.65	..			
6	Type 410	541000	0.15	1.00	0.040	0.030	1.00	11.5--13.5						
6F	Type 416	541600	0.15	1.25	0.060	0.15	1.00	12.0-14.0						
6F	"type 416Se	541623	0.15	1.25	0.060	0.060	1.00	12.0-14.0						Selenium, 0.15 min
7, 7M	Type 4140/4142/4145, 4140H, 4142H, 4145H		0.37--0.49	0.65--1.10	0.035	0.04	0.15--0.35	0.75-1.20		0.15--0.25	..			
8, 8A	Type 304	530400	0.08	2.00	0.045	0.030	1.00	18.0-20.0	8.0-11.0					
8C, 8CA	Type 347	534700	0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0-12.0	10 x carbon		
8J, 8MA	Type 316	531600	0.08	2.00	0.045	0.030	1.00	16.0--18.0	10.0-14.0	2.00-3.00	..			
8T, 8TA	Type 321	532100	0.08	2.00	0.045	0.030	1.00	17.0-19.0	9.0--12.0) x (C+N)		0.10	
														0.70
8F, 8FA	Type 303	530300	0.15	2.00	0.20	0.15 min	1.00	17.0--19.0	8.0-10.0					
8F, 8FA	Type 303Se	530323	0.15	2.00	0.20	0.06	1.00	17.0-19.0	8.0-10.0		...			Selenium, 0.15 min
8P, 8PA	Type 305	530500	0.08	2.00	0.045	0.030	1.00	17.0-19.0	11.0-13.0					
8N, 8NA	restricted carbon <N	... St	0.08	2.00	0.043	0.030	1.00	18.0-20.0	8.0-11.0				0.10-0.16	
8LN, 8LNA	Type 304LN	530453	0.030	2.00	0.045	0.030	1.00	18.0-20.0	8.0-11.0				0.10-0.16	
8MN, 8MNA	Type 316N	531651	0.08	2.00	0.045	0.030	1.00	16.0-18.0	10.0-13.0	2.011-3.00	..		6.16-0.16	
8MLN, 8MLNA	Type 316LN	531653	0.030	2.00	0.045	0.030	1.00	16.11-18.0	10.0-13.0	2.00--3.00	..		0.16-0.16	
8R, 8RA	XM19	520910	0.06	4.0--6.0	0.045	0.030	1.00	20.5-23.5	11.5--13.5	1.50--3.00	..	0.10--0.30	0.20-0.40	Vanadium,
6S, 8SA		521800	0.10	2.6-9.0	0.060	0.030	3.5-4.5	16.0-18.0	8.6-9.0				0.08--0.18	
SMLCuN, 8MI-CuN	531254	531254	0.020	1.00	0.030	0.010	0.80	19.5-20.5	17.5--18.5	6.0--6.5			0.18--0.22	Copper, 0.50-1.00
9C, 9CA	N08367	N06362	0.030	2.00	0.040	0.030	1.00	20.0-22.0	23.5- 25.5	6.0-7.0			0.18-0.25	Copper 0.75
16	Chromium Molybdenum Vanadium		0.36--0.47	0.45--0.70	0.035	0.040	0.15--0.35	0.80-1.13		0.50--0.65	..			Vanadium, 0.25-0.35 Aluminum 0.015

* The intentional addition of Bi, Se, Te, and Pb is not permitted except for Grades 6F, 8F, and 8FA, in which Se is specified and required.
 * Total aluminum, soluble and insoluble.
 °Maximum, unless minimum or range is indicated.
 °Where ellipses (...) appear in this table there is no requirement.
 * Because of the degree to which sulfur segregates, product analysis for sulfur over 0.060 % max is not technologically appropriate.
 * As described in Specification A 276.

280608

A 194/A 194M-08

8. Mechanical Requirements

8.1 *Hardness Test:*

8.1.1 *Requirements:*

8.1.1.1 All nuts shall meet the hardness requirements specified in Table 2.

8.1.1.2 Sample nuts of Grades 1, 2, 2H, 2HM, 3, 4, 7, 7M, and 16 which have been given the treatment described in 8.1.5 shall meet the minimum hardness specified in Table 2.

8.1.2 *Number of Tests*— (Grades 1, 2, 2H, 3, 4, 7, and 16 and all types of Grade 6):

8.1.2.1 Tests on the number of sample nuts in accordance with the following table shall be performed by the manufacturer following all production heat treatments:

Lot Size	Samples
Up to 800	1
801 to 8000	2
8001 to 22 000	3
over 22 000	s

8.1.2.2 In addition, a hardness test shall be performed by the manufacturer in accordance with 5.1.5 on one sample nut selected from each nominal diameter and series from each grade and heat number following completion of all production heat treatments.

8.1.3 *Number of Tests, Grades 2HM and 7M:*

8.1.3.1 Each nut shall be tested by Berett or Rockwell methods to ensure product conference.¹

8.1.3.2 In addition, 8.1.2.2 shall be met.

8.1.4 *Number of Tests, All Types of Grade 8*— Tests on the number of sample nuts in accordance with 8.1.2.1 shall be performed by the manufacturer.

8.1.5 *Test 2*— In addition to the testing required by 8.1.2.1 the manufacturer shall also perform hardness tests on sample nuts after the following test heat treatment. After completion of all production heat treatments heat the specimen nuts to the temperatures indicated below for 24 h, then slow cool. Test in room temperature.

Grade ¹	Temperature, °F [°C]
1	850 [455]
2, 2H, 2HM	1000 [540]
3, 4, 7, 7M	1100 [590]
16	1200 [650]

¹Nuts intended to be coated with zinc or cadmium (marked in accordance with the requirements of Supplementary Requirement S8) are not subjected to the requirements of 8.1.5 (See Appendix X2).

8.1.5.1 *Special Requirement, Grades 2HM and 7M*— Preparation of Grades 2HM and 7M nuts for hardness test and the hardness test itself shall be performed with consideration to (1) protect legibility of markings; (2) minimize exterior dimensional changes; and (3) maintain thread fit.

8.2 *Proof Load Test:*

8.2.1 *Requirements*— All nuts shall be capable of withstanding the proof loads specified in Table 3 and Table 4. However, nuts manufactured to dimensions and configurations other than those covered by ANSI J3 1.1, ANSIB 1.13M, ANSIB 18.2.2, and B 18.2.4.6M are not subject to the proof load test.

8.2.2 *Number of Tests:*

8.2.2.1 The manufacturer shall test the number of nuts specified in 11.1.2.1 following all production heat treatments. Nuts that would require a proof load in excess of 160 000 lb/f Or 705 kN may be furnished on the basis of minimum hardness requirements. Testing of nuts requiring a proof load in excess of 160 000 lb/f or 705 kN is covered in Supplementary Requirements S1 and 54.

8.2.3 *Test Method*— The test shall be run using a threaded mandrel Or a test bolt in accordance with Specification A 962/ A 962M.

8.3 *Cone Proof Load Test:*

8.3.1 *Requirements*— This test shall be performed only when visible surface discontinuities become a matter of issue between the manufacturer and the purchaser. Nuts in the size range 1/4 to 1 in. inclusive and M6 to M36 inclusive shall be proof load tested. Nuts not in this size range and all types of Grade 8 nuts are not subject to this test. Also, nuts manufactured to dimensions and configurations other than those covered by Specification A 962/A 962M, ANSI B 1.1, ANSI

¹An underline as a marking requirement for grades 2HM and 7M has been removed but is permitted.

TABLE 2 Hardness Requirements¹

Grade and Type	Brinell Hardness	Completed Nuts		Sample Nut after Treatment as in 8.1.5	
		Rockwell Hardness		Brinell Hardness, min	Rockwell Hardness B Scale, min
		C Scale	B Scale		
1	121 min		70 min	121	70
2	159 to 352		84 min	159	84
2H to 1/4 in. or M36, incl	248 to 327	24 to 35		179	89
2H over 1/4 in. or M36	212 to 327	35 max		147	79
2HM and 7M	159 to 235		95 min	159	84
3, 4, 7, and 16	248 to 327	24 to 35	84 to 99	201	94
6 and 6F	228 to 271	20 to 28			
8, 8C, 8M, 6T, 6F, 8P, 8N, 8MN, 8LN, 8MLN, 8MLCuN, and 9C	126 to 300	32 max	60 min		
8A, 8CA, 8MA, 8TA, 8FA, 8PA, 8NA, 8MNA, 8LNA, 8MLNA, 8MLCuNA, and 9CA	126 to 192		60 to 90		
8R, 8RA, 8S, and 8SA	183 to 271	25 max	88 min		

¹ Where ellipses (...) appear in this table there is no requirement.

SKE 280608

A 194/A 194M-08

TABLE 3 Proof Load Using Threaded Mandrel — Inch Series

Now I—Proof loads are not design loads.

Nominal Size, in.	Threads per Inch	Stress Area in. ²	Proof Load, lbf*					
			Grade 1		Grades 2, 2HM, 6, 6F, 7M		Grades 2H, 3, 4, 7, 16	
			Heavy Hex ^a	Hex ^c	Heavy Hex ^a	Next	Heavy Hex ^a	Next
1/4	20	0.0316	4 130	3 820	4 770	4 300	5 570	4 770
5/16	18	0.0524	6 810	6 290	7 660	7 070	9 170	7 860
3/8	16	0.0774	10 080	9 300	11 620	10 460	13 560	11 620
7/16	14	0.1063	13 820	12 760	15 940	14 350	18 600	15 940
1/2	13	0.1419	18 450	17 030	21 280	19 160	24 830	21 280
9/16	12	0.182	23 660	21 840	27 300	24 570	31 850	27 300
5/8	11	0.226	29 380	27 120	33 900	30 510	39 550	33 900
3/4	10	0.334	43 420	40 080	50 100	45 090	58 450	50 100
7/8	9	0.462	60 060	55 440	69 300	62 370	80 850	69 300
1	8	0.606	78 780	72 720	90 900	81 810	106 000	90 900
1 1/8	8	0.790	102 700	94 800	116 500	106 700	138 200	118 500
1 1/4	8	1.000	130 000	120 000	150 000	135 000	175 000	150 000
1 3/8	8	1.233	160 200	148 000	185 000	166 500	215 800	165 000
1 1/2	8	1.492	194 000	170 040	223 800	201 400	261 100	223 800

All Types of Grade 8, Grades 9C and 9CA					
			Heavy Hex ^o	Hex ^r	
1/8	20	0.0316	2540	2380	
5/16	18	0.0524	4190	3930	
3/8	16	0.0774	6200	5810	
7/16	14	0.1063	8500	7970	
1/2	13	0.1419	11350	10640	
5/8	12	0.182	14 560	13 650	
3/4	11	0.226	18 080	16 950	
7/8	10	0.334	26 720	25 050	
1	9	0.462	36 960	34 650	
1 1/8	8	0.606	48 480	45 450	
1 1/4	8	0.790	63 200	59 250	
1 3/8	8	1.000	80 000	75 000	
1 1/2	8	1.233	98 640	92 450	
1 5/8	8	1.492	119 360	111 900	

* See limit for proof load test in 8.2.2.1. The proof load for jam nuts shall be 46% of the tabulated load.
^a Based on proof stress of 130 000 psi.
^b Based on proof stress of 120 000 psi.
^c Based on proof stress of 150 000 psi.
^d Based on proof stress of 135 000 psi.
^e Based on proof stress of 175 000 psi.
^f Based on proof stress of 150 000 psi.
^g Based on proof stress of 80 000 psi.
^h Based on proof stress of 75 000 psi.

B I.13M, ANSI B 18.2.2, and ANSI B 15.2.4.6M are not subject to the cone proof load test. The cone proof load applied shall be determined in accordance with the Cone Proof Load requirements in Specification A 962/A 962M (tables or formulae or both) based upon the proof stresses shown in Table 5 and Table 6 of Specification A 194/A 194M.

11.3.2 Number of Fr.iix—The manufacturer shall sample and test the number of nuts specified in II. 1,2.1. The lot shall be considered acceptable if the sample nut(s) withstand(s) application of the cone proof load without failure.

9. Dimensions

9.1 Nuts shall be hexagonal in shape, and in accordance with the dimensions for the hex or heavy hex series, as

required, by ANSI B 1b.2.2 and ANSI B 18.2.4.6M. Unless otherwise specified, the American National Standard Heavy Hex Series shall be used and nuts shall be either double chambered or have a machined or forged washer face, at the option of the manufacturer, and, conform to the angularity requirements of ANSI D 1b.2.2 and ANSI B 18.2.4.6M.

9.2 Unless otherwise specified, threads shall be in accordance with ANSI B 1.1 or ANSI B 1.13M, and shall be gaged in accordance with ANSI B 1.2 and ANSI B 1. UM as described in 9.2.1 and 9.2.2.

9.2.1 Nuts up to and including 1 in. nominal size shall be UNC Series Class 2B fit. Metric nuts up to and including M24 nominal size shall be coarse thread series tolerance 6H.

SKE 280608

A 194/A 194M-08

TABLE 4 Proof Load Using Threaded Mandrel — Metric

Note I—Proof loads are not design loads.

Nominal Size, mm	Threads Pitch	Stress Area mmc	Proof Load, kN*					
			Grade 1		Grades 2, 2HM, 6, 6F, 7M		Grades 2H, 3, 4, 7, 16	
			Heavy Hex	Hex ^a	Heavy Hex ^c	Hex ^e	Heavy Hex ^g	Hex ⁱ
M6	1.0	20.1	18.0	16.6	20.8	18.7	29.2	20.8
M8	1.25	36.6	32.8	30.2	37.9	34.0	44.1	37.9
M10	1.50	58.0	51.9	47.9	60.0	53.9	69.9	60.0
M12	1.75	84.3	75.5	69.5	87.3	78.4	101.6	87.3
M14	2.0	115.0	102.9	94.9	119.0	107.0	138.6	119.0
M16	2.0	157.0	140.5	129.5	162.5	146.0	189.2	162.5
M20	2.5	245.0	219.3	202.2	253.6	227.8	295.2	253.6
M22	2.5	303.0	271.2	249.9	313.6	281.8	365.1	313.6
M24	3.0	353.0	315.9	291.2	365.4	328.3	425.4	365.4
M27	3.0	459.0	411.0	378.7	475.1	426.9	553.4	475.1
M30	3.5	561.0	502.1	462.8	560.6	521.7	676.0	580.6
M36	4.0	617.0	751.2	674.0	845.6	759.8	984.5	845.6

All Types of Grade 8, and Grades 9C and 9CA

Nominal Size, mm	Thread Pitch	Stress Area,	Heavy Hex ^a	Hex ^f
M6	1.0	20.1	11.1	10.4
MB	1.25	36.6	20.1	18.8
M10	1.50	58.0	31.9	29.9
M12	1.75	84.3	46.4	43.4
M14	2.0	115.0	63.3	59.2
M16	2.0	157.0	86.4	80.9
M20	2.5	245.0	134.8	126.2
M22	2.5	303.0	166.7	156.0
M24	3.0	353.0	194.2	181.8
M27	3.0	459.0	252.5	236.4
M30	3.5	561.0	308.6	288.9
M36	4.0	817.0	449.4	420.8

* See limit for proof load test in 8.2.2.1. The proof load for jam nuts shall be 46% of the tabulated load.

^aBased on proof stress of 895 MPa.

^cBased on proof stress of 825 MPa.

^eBased on proof stress of 1035 MPa.

^fBased on proof stress of 930 MPa.

^gBased on proof stress of 1205 MPa.

ⁱBased on proof stress of 1035 MPa.

^jBased on proof stress of 550 MPa.

^kBased on proof stress of 515 MPa.

TABLE 5 Proof Stress Using 120° Hardened Steel Cone — Inch

Type	Proof Stress - psi, Minimum		
	Graded	Grades 2, 2HM, 6, 6F & 7M	Grades 2H, 3, 4, 7, & 16
Hex	120 000	135 000	150 000
Heavy Hex	130 000	150 000	175 000

TABLE 6 Proof Stress Using 120° Hardened Steel Cone — Metric

Type	Proof Stress - MPa, Minimum		
	Grade 1	Grades 2, 2HM, 6, 6F & 7M	Grades 2H, 3, 4, 7, & 16
Hex	825	930	1035
Heavy Hex	895	1035	1205

A 194/A 194M - 08

TABLE 8 Proof Load Testing of Strain Hardened Nuts Using Threaded Mandrel — Inch Series

Note I—Proof loads are not design loads.

Nominal Size, in.	Threads per in.	Stress Area, in. ²	Proof Load, lbf*			
			Grade 8M (strain hardened)	Grade 8M (strain hardened)	All Other Types of Grade 8 (strain hardened)	All Other Types of Grade 8 (strain hardened)
			Heavy Hex ^a	Hex ^c	Heavy Hex ^o	Hex ^o
1/4	20	0.0316	3 480	3 160	3 950	3 480
5/16	18	0.0523	5 760	5 240	6 550	5 760
3/8	16	0.0774	8 510	7 740	9 675	8 510
7/16	14	0.1063	11 690	10 630	13 290	11 690
1/2	13	0.1419	15 610	14 190	17 740	15 610
5/16	12	0.182	20 020	18 200	22 750	20 020
3/8	11	0.226	24 860	22 600	28 250	24 860
1/2	10	0.334	36 740	33 400	41 750	36 740
3/8	9	0.462	46 200	41 580	53 130	46 200
1	8	0.606	60 600	54 540	69 690	60 600
1 1/8	8	0.790	75 050	67 150	82 950	75 050
1 1/4	8	1.000	95 000	85 000	105 000	95 000
1 3/8	8	1.233	110 970	98 640	123 300	110 970
1 1/2	8	1.492	154 280	119 360	149 200	134 280

*The proof load for jam nuts shall be 46% of the tabulated value.
 Based on proof stress of 110 000 psi up to 3/8 in.; 100 000 psi 1/2 to 1 in.; 95 000 psi 1 1/8 to 1 1/4 in.; 90 000 psi 1 1/2 to 1 3/4 in.
 Based on proof stress of 100 000 psi up to 3/8 in.; 90 000 psi 1/2 to 1 in.; 85 000 psi 1 1/8 to 1 1/4 in.; 80 000 psi 1 1/2 to 1 3/4 in.
^oBased on proof stress of 125 000 psi up to 3/8 in.; 115 000 psi 1/2 to 1 in.; 105 000 psi 1 1/8 to 1 1/4 in.; 100 000 psi 1 1/2 to 1 3/4 in.

TABLE 9 Proof Load Testing of Strain Hardened Nuts Using Threaded Mandrel — Metric

None I—Proof loads are not design loads.

Nominal Size, mm	Thread Pitch	Stress Area, mm ²	Proof Load, kN*			
			Grade 8M (strain hardened)	Grade 8M (strain hardened)	All Other Types of Grade 8 (strain hardened)	All Other Types of Grade 8 (strain hardened)
			Heavy Hex	Hex ^c	Heavy Hex ^o	Hex
M6	1.0	20.1	15.3	13.9	17.3	15.3
M8	1.25	36.6	27.8	25.3	31.3	27.8
M10	1.50	58.0	44.1	40.0	49.9	44.1
M12	1.75	84.3	64.1	58.2	72.5	64.1
M14	2.0	115.0	87.4	79.4	98.9	87.4
M16	2.0	157.0	119.3	108.3	135.0	119.3
M20	2.5	245.0	186.2	169.0	210.9	186.2
M22	2.5	303.0	209.0	187.9	240.9	209.0
M24	3.0	353.0	243.5	218.9	280.6	243.5
M27	3.0	459.0	300.6	268.5	332.7	300.6
M30	3.5	561.0	367.5	328.2	406.7	367.5
M36	4.0	817.0	506.5	449.4	563.7	506.5

*The proof load for jam nuts shall be 46% of the tabulated value.
 Based on proof stress of 760 MPa up to M20 mm; 690 MPa M22 to M24 mm; 655 MPa M27 to M30; and 620 MPa for M36. Based on proof stress of 690 MPa up to M20 mm; 620 MPa M22 to M24 mm; 585 MPa M27 to M30; and 550 MPa for M36.
^oBased on proof stress of 860 MPa up to M20 mm; 795 MPa M22 to M24 mm; 725 MPa M27 to M30 mm and 690 MPa for M36.

made in accordance with this requirement shall be marked with sizes larger than 1 1/2 in. and M36, which shall be subjected to the Grade symbol underlined. the tests specified in Section 8.

S2. Retests by Purchaser's Representative

52.1 The purchaser's representative may select two nuts per keg (200-lb unit [90-kg]) for sizes 5/8 in. and M16 and smaller, one nut per keg for sizes over 3/4 in. and M16 up to and including 1 1/2 in. and M36, and one nut per every two kegs for

S3. Low-Temperature Requirements for Grade 4, Grade 7 kN Grade 7M Nuts

53.1 When low-temperature requirements are specified for Grade 4 or Grade 7 nuts, the Charpy test procedures and requirements as defined in Specification A 320/A 320M for

SKE 280608

A 194/A 194M-08

Grade L7 shall apply. When low-temperature requirements are specified for Grade 7M nuts, the Charpy test procedures and requirements as defined in Specification A 320/A 320M for Grade L7M shall apply. Depending on the size of nuts, separate test samples of the same heat may be required and shall be processed through heat treatment with the nuts for which the test is to apply. Impact testing is not required when the bar stock or nut is smaller than 1/2 in. [16 mm] in diameter.

53.2 An "L" shall be added to the marking, as shown in Table 7, for nuts so tested.

54. Proof Load Tests of Large Nuts

54.1 Proof load testing of nuts requiring proof loads of over 160 000 lbf or 705 kN is required. Testing shall be performed in accordance with 8.2 to the loads required in Table 10 and Table 11. The maximum load will be based entirely on the equipment available.

55. Control of Product by Heat Number

55.1 When control of nuts by actual heat analysis is required and this supplementary requirement is specified, the manufacturer shall identify the completed nuts in each shipment by the actual heat number. When this supplementary requirement is specified, a certificate including the results of the actual production tests of each test lot together with the heat chemical analysis shall be furnished by the manufacturer.

56. Grain Size Requirements for Non-Hex Austenitic Steels Used Above 1000 °F

56.1 For design metal temperatures above 1000 °F [540 °C], the material shall have a grain size of No. 7 or coarser as determined in accordance with Test Methods E 112. The grain size so determined shall be reported on the Certificate of Test.

57. Coating on Nuts

57.1 It is the purchaser's responsibility to specify in the purchase order all information required by the coating facility. Examples of such information may include but are not limited to the following:

57.1.1 Reference to the appropriate coating specification and type, thickness, location, modification to dimensions, and hydrogen embrittlement relief.

Not 57.1—Modification of thread dimensions may result in loss of load carrying ability.

57.1.2 Reference to Specifications A 153/A 153M, B 695, B 696, B 76fi, F 1941, Test Method F 1940, or other standards.

58. Marking Coated Nuts

58.1 Nuts coated with zinc shall have an asterisk (*) marked after the grade symbol. Nuts coated with cadmium shall have a plus sign (+) marked after the grade symbol.

TABLE 10 Proof Load for Large Heavy Hex Nuts — Inch*

Nominal Size, in.	Threads per in.	Stress Area, in. ²	Proof Load, lbf*		
			Grade 1 Heavy Hex	Grades 2, 2HM, 6, 6F, 7M Heavy Hex	Grades 2H, 3, 4, 7, 16 Heavy Hex
1/4	8	1.78	231400	267 000	311 500
1/2	8	2.08	270400	312 000	364 000
3/8	8	2.41	313300	361 500	421 800
1/2	8	2.77	360100	415 500	484 800
3/4	8	3.56	462800	534 000	623 000
1	8	4.44	577200	666 000	777 000
1 1/4	8	5.43	705900	814 500	950 250

* ANSI B 18.2.2 in the size range over 1 1/2 in. provides dimensions only for heavy hex nuts. Refer to 8.3.1.

* Proof loads for nuts of larger dimensions or other thread series may be calculated by multiplying the thread stress area times the proof stress in the notes to Table 3 or Table 8. The proof load for jam nuts shall be 46% of the tabulated load.

SKE 280608

A 194/A 194M - 08

TABLE 11 Proof Load for Large Heavy Hex Nuts — Metric¹

Nominal Size, mm	Thread Pitch	Stress Area, mm ²	Proof Load, kN		
			Grade 4 Heavy Hex	Grades 2, 2HM, 6, 6F, 7M Heavy Hex	Grades 2H, 3, 4, 7, 16 Heavy Hex
M42	4.5	1120	1002.4	1159.2	1349.6
M48	5	1470	1315.7	1521.4	1771.4
M56	5.5	2030	1816.9	2101.0	2446.2
M64	6	2680	2398.6	2773.8	3229.4
M72	6	3460	3096.7	3581.1	4169.3

¹ ANSI B 18.2.4.6M in the size range over M36 provides dimensions only for heavy hex nuts. Refer to 7.3.1.
² Proof loads for nuts of larger dimensions or other thread series may be calculated by multiplying the thread stress area times the proof stress in the notes to Table 4 or Table 9. The proof load for jam nuts shall be 46% of the tabulated load.

APPENDIXES

(Nonmandatory Information)

XI. STRAIN HARDENING OF AUSTENITIC STEELS

XI.1 Strain hardening is the increase in strength and section reduction, die angle and bar size. In large diameter bars, hardness that results from plastic deformation below the recrystallization temperature (cold work). This effect is produced in austenitic stainless steels by reducing oversized bars to the desired final size by cold drawing or other process. The degree of strain hardening achievable in any alloy is limited by its strain hardening characteristics. In addition, the amount of strain hardening that can be produced is further limited by the variables of the process, such as the total amount of cross-section machined.

X2. COATINGS AND APPLICATION LIMITS

X2.1 Use of coated fasteners at temperatures above approximately one-half the melting point (Fahrenheit or Celsius) of the coating is not recommended unless given to the potential for liquid and solid metal embrittlement, or both. The melting point of elemental zinc is approximately 780 °F [415 °C]. Therefore, application of zinc coated fasteners should be limited to temperatures less than 390 °F [210 °C]. The melting point of cadmium is approximately 600 °F [320 °C]. Therefore, application of cadmium coated fasteners should be limited to temperatures less than 300 °F [160 °C].

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this specification since the last issue, A 194/A 194M—07b, that may impact the use of this specification. (Approved April 1, 2008)

(I) Added Nitrogen for Grades 8T and 8TA in Table 1.

Committee A01 has identified the location of selected changes to this specification since the last issue, A 194/A 194M—07a, that may impact the use of this specification. (Approved December 1, 2007)

(7) Added Note 57.1.

Committee A01 has identified the location of selected changes to this specification since the last issue, A 194/A 194M—07, that may impact the use of this specification. (Approved March 1, 2007)

(I) Added reference to Test Method F 1940 in 57.1.2.

A 194/A 194M – 08

Committee A01 has identified the location of selected changes to this specification since the last issue, A 194/A 194M—06a, that may impact the use of this specification. (Approved February 1, 2007)

SKE 280608

(2) Revised cone proof load test requirements to reference recent changes to Specification A 962/A 962M and Test Methods and Definitions A 370.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, 60158. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail), or through the ASTM website